

## LOXEAL UV 30-23

### Description

Very low viscosity, fast curing, high strength Ultra Violet curing adhesive. Specially designed for bonding float glass to glass in the manufacturing of glass and crystal furniture.

### Physical properties

Composition:	methacrylate ester
Colour :	colourless
Viscosity (Brookfield 25°C–mPa.s):	50 - 100
Specific weight (g/ml):	1,1
Curing time UV (365 nm):	8 - 15 seconds
Gap to fill:	from 0,03 mm to 1,5 mm
Flash point:	> 100°C
Shelf life :	1 year

### Curing properties

For better strength and durability we recommend to clean, degrease and dry surfaces to bond. The polymerisation UV is belonging to the intensity of the UV lamp, to the distance from the UV light source, to the bondline gap and to the light transmittance of the substrate the light shall pass through. We recommend high intensity UV light sources with minimum radiation between 365 nm and 420 nm at 100mW/cm<sup>2</sup>. Curing time may vary according to adhesive gap.

### Properties of cured adhesive

* Tensile strength (ASTM D-2095-69):	10 - 14 N/mm <sup>2</sup>
* Temperature range:	-55°C + 120°C
* Refractive index:	1,49
* Light transmittance:	> 90%
* Coefficient of thermal expansion:	85 x 10 <sup>-6</sup> mm/mm/°C
* Dielectric constant ( 25°C 1000 Hz):	4
* Dielectric strength	10-12 KV/mm

### Storage

Keep product in a cool and dry room at +28°C. To avoid contaminations do not refill containers with used product. For more information on applications, storage and handling contact Loxeal Technical Service

### Safety and handling

Consult Material Safety Data Sheet

### Note

The data contained herein, obtained in Loxeal laboratories, are given for information only. Loxeal cannot assume responsibility for the results obtained by others which methods are not under Loxeal control. It is the user's responsibility to determine suitability for the user's purpose of any product mentioned herein. Loxeal disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Loxeal products. Loxeal specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.